

Deck-Lok™

100% Acrylic Latex Paint

TECHNICAL DATA SHEET

Available in Smooth or Textured Formula



Rain Guard Pro® Deck-Lok™

Description

Deck-Lok™ is an interior/exterior 100% acrylic latex paint. The excellent adhesion, durability, and resistance to alkalinity makes this an ideal all purpose floor finish for all wood, masonry, and metal substrates. The durable latex film dries to a soft low sheen finish and may be walked on in 24 hours, depending on drying conditions.

PLEASE NOTE: This product is NOT intended for surfaces with vehicular or other hot tire traffic. Please see Rain Guard Pro® Clear-Seal™ 100% or Polyurethane HD products for these types of applications.

Features

- Tough and durable finish
- Eco-friendly and low odor
- For horizontal or vertical application
- Excellent adhesion to a variety of surfaces
- Unlimited color selection
- Water and scratch resistant
- Resists fading and chalking
- Dries to a low sheen
- Available in smooth or textured formula

Recommended Uses

- Decks & Patios
- Metal Trim
- Walls & Floors
- Swimming Pool Areas
- Walkways
- Wooden Fences & Gates

Test Panel

Always apply material to a mock wall or test panel. Test wall or actual surface area to determine acceptable color, surface porosity, application rates and methods before starting general application.

Inspection

All cracks (other than hairline) should be pointed or caulked. All voids and bee holes or other masonry surface defects should be repaired using knife or brushgrade elastomeric, urethane, or other approved patching. Defective mortar joints should be routed out, pointed with mortar, or caulk and tooled. *(continued)*

Seal or caulk all exterior openings such as conduits, pipes, drains, door frames, vents, air conditioner openings, electrical openings, control joints, or any dissimilar materials, using urethane or elastomeric, or any approved caulk or sealer. Allowing patching materials and sealers to cure prior to application of water repellents and/or Deck-Lok™. All surfaces to be coated should be structurally sound, clean, and dry. Kill mold, mildew, and fungus using commercially available cleaners or a 50/50 mix of bleach and water. Make sure all residue is rinsed prior to coating application. Mix contents thoroughly prior to application. To prevent skinning, cover pail with a damp cloth.

Coverage - Deck-Lok™ Smooth

Actual coverage rates may vary due to surface textures.

Substrate	Sq Ft / Gallon
Wood	400
Concrete	300-400
Masonry	300-400
Asphalt	300
Metal	400

Coverage - Deck-Lok™ Textured

Actual coverage rates may vary due to surface textures.

Substrate	Sq Ft / Gallon
Wood	200
Concrete	150-200
Masonry	150-200
Asphalt	150
Metal	200



RainguardPro® Deck-Lok™

Application

All surfaces must be free of dirt, grease, wax, mildew, chalk, loose peeling paint or any other contaminants. Deck-Lok™ is ready to use out of the can. If thinning is required use a small amount of water. For best results two coats of Deck-Lok™ are recommended. (See page 3 for details)

1. Apply Deck-Lok™ at outdoor temperatures between 50°F - 100°F
2. New unpainted surfaces should be properly primed with a primer such as RainguardPro® Micro-Seal®.
3. To avoid lap marks, maintain a continuous wet edge. Feather edges at the end of each pass.
4. Stop application only at control joints, corners, and edges. Back rolling may be necessary to even the applied finish.

Deck-Lok™ may be applied by using:

Brush - synthetic or nylon bristled brush
 Roller - 1/4" nap for smooth surface or 3/8" to 1/2" nap for rough surfaces

Drying Time

Allow approx. 30 min to 1 hr at 75°F for Deck-Lok™ to be dry to the touch. Allow approx. 24 hours at 75°F for Deck-Lok™ to be walked on.

Clean Up

Uncured material can be removed with soap and water. Cured material can only be removed mechanically. All empty containers must be disposed of according to local, state, and federal regulations.

Limitations

The information contained herein is offered in good faith and is believed to be accurate. To be eligible for a Rainguard Warranty the following must occur:

1. A site visit must be conducted by an employee or agent of Rainguard and a Field Inspection Report completed.
2. A Warranty Application must be fully completed by the applicator.
3. Field Inspection Report, Warranty Application, and a copy of the distributor's invoice must be submitted to and approved by Rainguard.

This material is only warranted when applied in accordance with the manufacturer's guidelines and warranty procedures. Without adherence to these specific guidelines, no expressed or implied warranty of this product is given. Please contact Rainguard for additional information.

	Product	U/M	Code	
SMOOTH	White	1 Gallon	DL-0101-WT	
	White	5 Gallon	DL-0105-WT	
	Black	1 Gallon	DL-0201-BK	
	Black	5 Gallon	DL-0205-BK	
	Mission Brown	1 Gallon	DL-0301-MB	
	Mission Brown	5 Gallon	DL-0305-MB	
	Patio Grey	1 Gallon	DL-0401-PTG	
	Patio Grey	5 Gallon	DL-0405-PTG	
	Brick Red	1 Gallon	DL-0501-BR	
	Brick Red	5 Gallon	DL-0505-BR	
	Terrace Green	1 Gallon	DL-0601-TG	
	Terrace Green	5 Gallon	DL-0605-TG	
	Pebble Grey	1 Gallon	DL-0701-PG	
	Pebble Grey	5 Gallon	DL-0705-PG	
	Suede	1 Gallon	DL-0801-SD	
	Suede	5 Gallon	DL-0805-SD	
	TEXTURED	White	1 Gallon	DL-1101-WT
		White	5 Gallon	DL-1105-WT
Black		1 Gallon	DL-1201-BK	
Black		5 Gallon	DL-1205-BK	
Mission Brown		1 Gallon	DL-1301-MB	
Mission Brown		5 Gallon	DL-1305-MB	
Patio Grey		1 Gallon	DL-1401-PTG	
Patio Grey		5 Gallon	DL-1405-PTG	
Brick Red		1 Gallon	DL-1501-BR	
Brick Red		5 Gallon	DL-1505-BR	
Terrace Green		1 Gallon	DL-1601-TG	
Terrace Green		5 Gallon	DL-1605-TG	
Pebble Grey		1 Gallon	DL-1701-PG	
Pebble Grey		5 Gallon	DL-1705-PG	
Suede		1 Gallon	DL-1801-SD	
Suede		5 Gallon	DL-1805-SD	

Technical Data // Deck-Lok™ Smooth

Solvent	Water
Finish	Low Sheen
Resin Type	100% Acrylic Resin
VOC	49 g/L
Viscosity	85-90 KU
Weight Per Gallon	10.30 lb +/- 2%
Solids By Weight	47.00 % +/-2%
Solids By Volume	35.00 % +/-2%
Dry Time*	To touch - 1/2 hour; To recoat - 2 hours
DFT	1.40 mil
Thinning	If needed, may be thinned with 8oz water
Application Temperature**	Anywhere between 50°F - 100°F

**depending on temperature and humidity*

***keep product from freezing*

Technical Data // Deck-Lok™ Textured

Solvent	Water
Finish	Textured - Slight Sheen
Resin Type	100% Acrylic Resin
VOC	43 g/L
Viscosity	110-120 KU
Weight Per Gallon	11.60 lbs +/- 2%
Solids By Weight	60.70 % +/-2%
Solids By Volume	47.90 % +/-2%
Dry Time*	To touch - 1 hour; To recoat - 4 hours
DFT	3.84 mil
Thinning	If needed, may be thinned with 8oz water
Application Temperature**	Anywhere between 50°F - 100°F

**depending on temperature and humidity*

***keep product from freezing*



RainguardPro® Deck-Lok™